THE EUCLID CHEMICAL COMPANY



19218 REDWOOD ROAD • Cleveland, OH 44110 (216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596 www.euclidchemical.com

EUCOLITH "R"

* * * * * * *

CONCRETE BLOCK PLASTICIZER

XENG.SPECS◆CATALOG INDEX♦MSDS◆SECTION INDEXXFRENCH◆PRINT♦SPANISH♦EXIT CATALOG

EUCOLITH "R" is an ammoniated ethanol sulfonate designed to aid in the production of machine formed concrete products. Its plasticizing action improves the appearance, moldability and green strength of the products. Its cement dispersing properties assist in greater utilization and hydration of the cement and in increased compressive strengths. EUCOLITH "R" is ready to use and does not require agitation or further mixing. EUCOLITH "R" is not a soap nor does it contain calcium chloride.

PRIMARY APPLICATIONS

- Block
- Pipe
- Split block
- Slump brick
- Tile
- Precast concrete

FEATURES / BENEFITS

- Plasticizes for easy stripping and increased production
- Improves texture and lightens color
- Improves green strength and makes for easier handling
- · Improves cohesiveness and reduces cracking
- · Higher final compressive strengths
- Denser, more watertight unit

PACKAGING

EUCOLITH "R" is packaged in bulk, 275 gal (1041 liter) totes, 55 gal (208 liter) drums and 5 gal (18.9 liter) pails.

TECHNICAL INFORMATION

Typical Engineering Data

8" X 8" x 16" Unit - 1400 lb sand, 1200 lb gravel (203 x 203 x 406 mm) (635 kg) (544 kg)

Mix	Average	Average	Cement	Eucolith
	Wt.	psi		
1	38.62 lb	2125	325 lb	10 oz
	(17.5 kg)	(15 MPa)	(147 kg)	(296 ml)
2	37.60 lb	1705	300 lb	9 oz
	(17.1 kg)	(12 MPa)	(136 kg)	(266 ml)
3	37.68 lb	1572	300 lb	none
	(17.1 kg)	(11 MPa)	(136 kg)	

8" X 8" X 16" - 1700 lb sand, 2600 lb solite (203x203x406 mm) (771 kg) (1179 kg)

	Avg				
	<u>Mix</u>	<u>psi</u>	Cement	Eucolith	<u>flour</u>
1	30.75 lb	1372	300 lb	15 oz	170 lb
	(13.95 kg)	(9.46 MPa)	(136 kg)	(444 ml)	(77 kg)
2	30.00 lb	1191	280 lb	15 oz	150 lb
	(13.61 kg)	(8.21 MPa)	(127 kg)	(444 ml)	(68 kg)
3	30.33 lb	1134	280 lb	12 oz	150 lb
	(13.76 kg)	(7.82 MPa)	(127 kg)	(355 ml)	(68 kg)
4	30.33 lb	1134	300 lb	none	170 lb
	(13.76 kg)	(7.82 MPa)	(136 kg)		(77 kg)

Appearance

EUCOLITH "R" is a light yellow, free flowing liquid which when added to concrete, does not change the concrete's natural appearance.

Shelf life is 2 years in original, unopened package.


DIRECTIONS FOR USE

EUCOLITH "R" is used at a rate of 2 1/2 to 4 oz/100 lb (155-250 ml/100 kg) of cement depending on the mix design and type of aggregate being used. EUCOLITH "R" can be added to each batch of concrete either manually or with automatic dispensing equipment. EUCOLITH "R" should be added with the water for immediate dilution and distribution throughout the batch.

PRECAUTIONS / LIMITATIONS

• Protect from freezing.





WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with his warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.