THE EUCLID CHEMICAL COMPANY



19218 REDWOOD ROAD • Cleveland, OH 44110 (216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596 www.euclidchemical.com

EUCON 11

* * * * * * *

ADMIXTURE FOR IMPROVING CONCRETE

XENG.SPECS ◆CATALOG INDEX

♦MSDS ♦SECTION INDEX

XFRENCH ◆PRINT

XSPANISH ◆EXIT CATALOG

EUCON 11 is a liquid admixture designed to accelerate the setting time of concrete and particularly that of fly ash concrete while producing higher early and ultimate strengths. It is non-staining and therefore suitable for use in architectural concrete. EUCON 11 can be used with air entraining cements and with air entraining, waterproofing and calcium chloride admixtures. However, each admixture must be dispensed separately into the concrete mix.

PRIMARY APPLICATIONS

- General purpose ready mixed concrete
- · Concrete containing fly ash
- Architectural concrete

FEATURES / BENEFITS

Plastic Concrete

- Reduces bleed water
- Reduces segregation
- Reduces water requirements
- Improves workability.

Hardened Concrete

- Increases strengths at all ages
- Improves finished appearance
- Reduces cracking
- Reduces permeability
- Non staining

SPECIFICATIONS / COMPLIANCES

EUCON 11 is formulated to meet the requirements of ASTM C-494, Type A and AASHTO M-194.

PACKAGING

EUCON 11 is packaged in bulk, 275 gal (1041 liter) totes, 55 gal (208 liter) drums and 5 gal (18.9 liter) pails.

Dosage Rates

EUCON 11 is normally used at dosages of 3 to 5 fluid oz per 100 lb (190-315 ml/100 kg) cement. Dosage recommendations depend on the characteristics of the materials being used.

TECHNICAL INFORMATION

Typical Engineering Data Initial Setting Rate @ 75°F (24°C)

Mix	Cement	Fly Ash	Time	
	lb (kg)	lb (kg)		
Reference	517 (235)		4 hr	
EUCON 11	423 (192)	80 (36)	3 hr 40 min	
EUCON 11	470 (213)		3 hr 40 min	

Strength Comparison

Mix	Cement	Fly Ash	Slump	Air	Increase
	lb (kg)	lb (kg)	in (mm)	%	%
Reference	470 (213)		3 1/2 (8.9)	4.8	
EUCON 11	423 (192)		4 1/2 (11.4)	5.6	110-130
EUCON 11	376 (170)	80 (36)	4 1/2 (11.4)	5.3	110-130

Shelf life is 2 years in original, unopened package.


DIRECTIONS FOR USE

EUCON 11 should be added to the sand or water. It should not come in contact with dry cement or other admixtures until they are mixed in the concrete batch. EUCON 11 is dispensed with automatic equipment, thus insuring uniformity of admixture dosage throughout the job.

PRECAUTIONS / LIMITATIONS

- Care should be taken to maintain EUCON 11 above freezing.
- For additional information on EUCON 11, its usage on typical mix designs, contact The Euclid Chemical Company.
- Add to mix independent of other admixtures.
- EUCON 11 contains added chlorides and adds approximately 18 ppm calcium chloride to a yd³ (.76 m³) of 3000 psi (20.7 MPa) concrete.





WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any wirten or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.