

THE EUCLID CHEMICAL COMPANY

19218 REDWOOD ROAD • Cleveland, OH 44110 (216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596 www.euclidchemical.com

EUCOSLIP VOX

XENG.SPECS	♦CATALOG INDEX
♦MSDS	♦SECTION INDEX
X FRENCH	♦PRINT
XSPANISH	♦EXIT CATALOG

V.O.C. COMPLIANT FORM RELEASE AGENT

EUCOSLIP VOX is a concrete form coat consisting of a blend of proprietary vegetable oils and mineral oil. EUCOSLIP VOX is suitable for use with many types of concrete forms including wood, steel and aluminum formliner of fiberglass and PVC.

PRIMARY APPLICATIONS

- Form release for metal, wood, plastic and fiberglass forms
- · Concrete molds, overlaid plywood and fiberglass
- Equipment maintenance-scoots, bucket hoists and paving machines
- Aluminum and steel windows

FEATURES / BENEFITS

- Can be applied in sub-freezing or very hot temperatures
- Does not cause efflorescence
- Reduces imperfections on hardened surface
- Free of waxes and silicones
- Non-staining
- Preserves wood forms
- Economical to use

SPECIFICATIONS / COMPLIANCES

- Corps of Engineers CE-204, Section 7.10
- Corps of Engineers CE-1401.01, Section 17.4
- This product meets V.O.C. contents in accordance to EPA 40 CFR Part 59 Table I Subpart D for Form Release Compounds with a maximum V.O.C. content of 450 g/l

PACKAGING

EUCOSLIP VOX is packaged in 55 gal (208 liter) drums and 5 gal (18.9 liter) pails.

COVERAGE

Form Surface	<u>ft²/gal (m²/liter)</u>
Non-porous	1,500 (37)
Pre-oiled Plywood	1,000 (25)
Untreated Plywood	700 (17)

TECHNICAL INFORMATION

Typical Engineering	Data
Freeze Temperature	e15°F (-26 °C)
Freeze Damage	None
Boiling Point	>250°F (121°C)
	175°F (79°C)
	s) 15 @ 68°F (20°C)
Solids	None
Specific Gravity	0.885
Pounds per Gallon	
V.O.C.	
Compatibility Table	-
Plywood	All grades, Pre-oiled
	Overlaid (LDO,MDP,HDO)
Plastics	Fiberglass, reinforced,
	ABS, PVC
	Epoxy, Urethane
Elastomerics	Urethane, Silicone
Steel	All types
Aluminum	All types
Wood	All types

Shelf life is 1 year in original, unopened package.

Appearance

EUCOSLIP VOX is a free flowing light brown liquid. EUCOSLIP VOX will not stain gray or white concrete. For the best appearance on formed concrete surfaces, a very thin film of EUCOSLIP VOX should be applied with a sprayer, brush or roller. Excess application of form oil may cause "bugholes" or imperfections. At low temperatures below 45°F (7°C), increase normal sprayer pressure about 10 psi (.07 MPa) to obtain film thickness required.

DIRECTIONS FOR USE

Surface Preparation-For best results, forms should be cleaned of all old concrete before application of EUCOSLIP VOX.

Mixing-EUCOSLIP VOX requires no pre-mixing before application. The product should be used directly from the container. **Placement**-EUCOSLIP VOX is applied by brush, roller or pump-up type sprayer. Coated forms may be used 1/2 hour after application of EUCOSLIP VOX

CLEAN-UP

Clean tools and equipment with solvent such as EUCO SOLVENT, xylene or toluene.

PRECAUTIONS / LIMITATIONS

- Do not use on form/formliners made from SBR, natural rubber, latexes or from expanded poly sty-rene.
- At subfreezing temperatures form oil thickens and care should be taken to maintain proper coverage rate.
- Do not dilute EUCOSLIP VOX with fuel oil, diesel or mineral spirits.
- Keep out of reach of children.
- Avoid prolonged contact with skin.
- Use with adequate ventilation.
- Always wear protective clothing (rubber gloves, eye protection, etc...).
- Do not use as a bond breaker for tilt-up concrete construction.

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MARCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall have shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.