



THE EUCLID CHEMICAL COMPANY

19218 REDWOOD ROAD • Cleveland, OH 44110
(216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596
www.euclidchemical.com

FIBERSTRAND 150



POLYPROPYLENE MICRO FIBER REINFORCEMENT

- ◆ ENG. SPECS
- ◆ MSDS
- ◆ FRENCH
- ◆ XSPANISH
- ◆ CATALOG INDEX
- ◆ SECTION INDEX
- ◆ PRINT
- ◆ EXIT CATALOG

FIBERSTRAND 150 is an engineered polypropylene fiber designed specifically for secondary reinforcing of concrete. FIBERSTRAND 150 fibers are true monofilaments that totally disperse into the concrete mix when added at the batch plant or at the job site. FIBERSTRAND 150 is available in various lengths to provide optimum strength, reduced cracking and long-term concrete durability.

PRIMARY APPLICATIONS

- Flatwork industrial, commercial and residential concrete projects
- Footings, foundations, walls and tanks
- Concrete pipe, burial vaults and prestressed beams

FEATURES / BENEFITS

Plastic Concrete

- Controls or eliminates plastic shrinkage cracks
- Reduces segregation
- Minimizes bleed water
- Provides three-dimensional reinforcing versus two-dimensional with wire mesh

Hardened Concrete

- Reduces cracking
- Increases surface durability
- Reduces permeability
- Increases post-crack strengths

Other

- Reduces in-place cost versus concrete with wire mesh
- Faster form removal
- Totally safe compared to extruded reinforcing mesh
- Easy to use and can be added to the concrete mix at any time prior to concrete placement

SPECIFICATIONS/COMPLIANCES

- Complies with ASTM C-1116, Type III, Synthetic Fiber-Reinforced Concrete and Shotcrete

TECHNICAL INFORMATION

Typical Engineering Data

Material	Polypropylene
Specific Gravity	0.92
Alkali Resistance	Excellent
Acid Resistance	Excellent
Thermal Conductivity*	7
Mildew Resistance	Excellent
Fiber Length	3/4"(19 mm)
Denier	4
Fiber Count.....	over 50 million per lb (0.45 kg)
Fiber Type	Monofilament
Density	57 lb/ft ³ (915 kg/m ³)
Color	White
Absorption	Nil
Tensile Strength	3.0 gr/denier min
Modulus of Elasticity.....	0.55 x 10 ⁶ psi (3793 MPa)
Ignition Point.....	Over 1,000°F (538°C)
Melt Point	325°F (163°C)
Electrical Conductivity	Low
Dosage Rate ...	0.5 - 1.0 lb/yd ³ (0.3 - 0.6 kg/m ³)
Standard Dosage.....	1.0 lb/yd ³ (0.6 kg/m ³)


* Air equals 1, polypropylene equals 7.

PACKAGING

FIBERSTRAND 150 is packaged in 0.5 lb (0.23 kg) water dispersible bags.

DIRECTIONS FOR USE

FIBERSTRAND 150 can be added any time prior to placement of the concrete. It is recommended that it be added at the ready-mix concrete plant during batching, but it can work equally well when introduced at the job site. FIBERSTRAND 150 must be mixed with the concrete for a minimum of 3 minutes at maximum drum speed to assure total dispersion and uniformity.



Form Fiberstrand 150- 8.00

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.