

### THE EUCLID CHEMICAL COMPANY

19218 REDWOOD ROAD • Cleveland, OH 44110 (216) 531-9222 • (800) 321-7628 • FAX (216) 531-9596 www.euclidchemical.com

# VISCTROL

VISCOSITY MODIFYING ADMIXTURE

**VISCTROL** is a ready to use liquid admixture designed to modify the viscosity of self compacting concrete. When VISCTROL is used in conjunction with superplasticizing admixtures, 18"-28" (460-710 mm) diameter spreads are achieved without segregation or lowering compressive strengths.

#### **PRIMARY APPLICATION**

• Self compacting concrete

#### FEATURES/BENEFITS

- Greatly reduces or eliminates bleeding or segregation
- Evenly disperses aggregates within mix
- Eliminates need for vibration
- Provides superior slump retention
- Eliminates segregation during pumping
- Easily metered with standard admixture dispensing equipment

#### **APPEARANCE**

VISCTROL is a medium viscosity, dark brown liquid which will not discolor concrete.

#### PACKAGING

VISCTROL is packaged in 275 gallon (1041liter) totes, 55 gallon (208 liter) drums and 5 gallon (18.9 liter) pails.

XENG.SPECS	<b>♦CATALOG INDEX</b>
♦MSDS	<b>♦</b> SECTION INDEX
<b>X</b> FRENCH	♦PRINT
SPANISH	<b>◆EXIT CATALOG</b>

## TECHNICAL INFORMATION

**Mix Proportions** 

See your local Euclid Chemical Company Representitive

#### **Batching Sequence**

The batching sequence in a SCC system is critical to optimize performance of each admixture introduced. Laboratory data has shown the following order of addition to be effective:

- 1.) Air Entraining Agent (optional)
- 2.) VISCTROL
- 3.) Water Reducers
- 4.) Accelerator or Retarder (optional)

#### **Typical Dosages**

Dosages of VISCTROL will vary widely depending on W/C ratio and the gradation of the materials used. Consult your Euclid Chemical representitive for appropriate dosing suggestions.

The following doses are suggestions based on W/C ratio:

<u>W/C</u> .35 -.40 .40 -.45 Ounces/yd3(mls/m3) 2-20 (77-775) 20-60 (775-2320)

#### PRECAUTIONS/LIMITATIONS

- Agitate VISCTROL before use
- Do not allow material to freeze
- Air entraining agents must be added first
- Superplasticizers must be used to increase slump after the addition of VISCTROL
- Slight set retardation may occur with the use of this product





Form Visctrol -9.01

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for six (6) months from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within on (1) year from the date of the claimed breach. Euclid products which fails to conform with such installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.